

Tnemec General Structural Steel Coatings Schedule

STRUCTURAL STEEL PROTECTIVE COATINGS

1.0 STANDARD STEEL - COATING SYSTEMS

Standard Shop Primer shall conform to the following performance criteria; Tnemec Series 394 PerimePrime is used as standard of quality and performance. Meets requirements of LEED V4 and red list free.

Performance Criteria:	Apply one coat at 2.5-3.5 mils DFT.
Adhesion ASTM 4541:	Requirement- Not less than 1150 psi
Fire Proofing/Compatibility ASTM E736:	Requirement- Must meet ambient bond for Monokote MK-6, 2106 and 2146, Isolatak Blazeshield II and Cafco 300.
Humidity ASTM 4585:	Requirement- No more than one (1%) percent rust after 5000 hours exposure.
Impact ASTM-D 2794:	Requirement- No visible cracking or delamination after 160 lbs. inches direct impact.
UL 263 ASTM E 119:	Requirement- Must pass two (2) hour UL classified for use under WR Grace Monokote MK65/H4. Isolatak Blazeshield fire resistant materials.
Salt Spray ASTM B117:	Requirement- No more than 3% rust or plane. No more than 1/64" creepage at scribe after 10,250 hours.
Class B Slip Criteria:	SSPC-SP3 Power Tool Cleaning. Must meet slip coefficient of .056.
SENAC Complaint	Meets SENRAC OSHA; ASTM F1679 and ASTM F1677.

2.0 ARCHITECTURALLY EXPOSED STEEL

System #1

(2 coats in shop system.)

Primer: Tnemec Series 90G-1K97, H90-97 Tnemec-Zinc or Series 94-H20 Hydro-Zinc. Apply at 2.5-3.5 mils DFT.

Epoxy Intermediate: Tnemec Series 66HS Hi-Build Epoxoline or Series 161HS Tnemec-Fascure

(Field finish may be required) Apply at 4.0-6.0 mils DFT.

System #2

(3 coat shop applied system)

Primer:

Tnemec Series 90G-1K97, Series H90-97 Tnemec-Zinc or Series 94-H₂O Hydro-Zinc. Apply at 2.5-3.5 mils DFT.

Epoxy Intermediate:

Tnemec Series 66HS Hi-Build Epoxoline or Series 161HS Tnemec-Fascure. Apply at 4.0-6.0 mils DFT.

Urethane Topcoat:

Tnemec Series 1095 Endura-Shield. Apply at 2.5-3.0 mils DFT.

END OF SECTION

Specifier Notes: This product selection guide is written according to the Construction Specifications Institute (CSI) Format, including *Master Format*, *Section Format*, and *Page Format*, contained in the *CSI Manual of Practice*.

The section must be carefully reviewed and edited by the Architect to meet the requirements of the project and local building code. Coordinate this section with other specification sections and the drawings.

Delete all "Specifier Notes" when editing this section.

Specifier Notes: This section covers Tnemec high-performance coating systems for commercial facilities.

This schedule is only a guide listing various coating system options for various environments and should not be used as a final specification. Additional coating systems not listed in this schedule are available and may be more appropriate for your coating application. To finalize this coatings schedule, please contact www.rightergroup.com

Most coatings specified contain organic solvents. Consult Righter Group for compliance to local VOC regulations.

Righter Group, Incorporated
187 Ballardvale Street, Suite A190
Wilmington, MA 01887
Phone: (800) 533-3003 Fax: (800) 988-9824

March 2018